

KUREZ DR VOX

DISSIPATING CURING COMPOUND



EUCLID CHEMICAL

PACKAGING

275 gal (1040.9 L) tote (MTO)

Code: 157D 27

55 gal (208 L) drums

Code: 157D 55

5 gal (18.9 L) pails

Code: 157D 05

CLEAN UP

Warm, soapy water

(see "Clean-Up and Removal")

SHELF LIFE

2 years when stored properly

SPECIFICATIONS AND COMPLIANCES

- VOC Content: 301 g/L
- ASTM C309, Types 1 and 1-D, Classes A & B
- AASHTO M 148, Types 1 and 1-D, Classes A & B
- CDPH Standard Method v1.2, 2017
- USGBC LEED Version 4, BD&C, ID&C
- The Well Building Standard
- NTPEP tested and approved
- ANSI/GBI 01, Green Building Assessment Protocol

DESCRIPTION

KUREZ DR VOX is a water-based resin, reduced odor, liquid membrane forming curing compound formulated with dissipating agents. KUREZ DR VOX provides an excellent initial cure for concrete, then it begins to break down and deteriorate upon exposure to traffic and UV light. After cleaning to completely remove the KUREZ DR VOX, the concrete is ready for the application of coverings, coatings, or sealers.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Use of this product ensures proper curing resulting in stronger, more wear-resistant concrete
- Helps to minimize dusting
- Film breaks down when exposed to UV & traffic
- Available in a fugitive dye formulation

PRIMARY APPLICATIONS

- Curing interior or exterior* concrete
- Concrete that will later receive a covering or coating
- Where a long term membrane film is not desired on the concrete surface

** Product film will discolor when exposed to sunlight*

APPEARANCE

KUREZ DR VOX may vary from off white to pale yellow. Color variation does not affect product performance. KUREZ DR VOX may turn a deeper amber color upon exposure to UV light.

APPLICATION PROPERTIES

These properties are based on laboratory conditions at 73°F, 50% RH. Expect variation based on jobsite conditions.

COVERAGE

For good dissipation and easy removal, do not apply at a thicker film than indicated.

Drying time:

1 hour

Foot Traffic:

2 to 4 hours

Wheel Traffic:

6 to 10 hours

Moisture Loss (ASTM C156):

< 0.55 kg/m²

Textured Concrete:

300 ft²/gal (7.4 m²/L)

Smooth Concrete:

400 ft²/gal (9.8 m²/L)

DIRECTIONS FOR USE

Surface Preparation: As soon as possible after final troweling (or stripping of forms in vertical applications), apply KUREZ DR VOX at the recommended coverage rate.

Mixing: Material may separate during long term storage. Mild agitation or mixing is required before use.

Application: Apply at a uniform coverage by spray or roller application. Product may be sprayed with a hand held "pump-up" sprayer or an airless industrial sprayer. On vertical surfaces such as walls and columns, KUREZ DR VOX should be applied immediately after forms are stripped. **Do not apply at a thicker film than the suggested coverage rates allow. Heavy or uneven application can result in slow dissipation, difficult removal of the KUREZ DR VOX, and may discolor the concrete surface.** On interior hard troweled floors where a liquid densifier will be applied (and with approval from the project engineer), the coverage rate of KUREZ DR VOX may be increased to 400 ft²/gal (9.8 m²/L) in order to facilitate easier removal.

Dissipation: The exact time for dissipation/break down of KUREZ DR VOX will vary depending on application rate, moisture level in the concrete, and the amount of exposure to UV light and construction traffic. KUREZ DR VOX will continue to dissipate and become increasingly easier to remove as time passes. Floors to receive coatings, sealers and coverings must be cleaned thoroughly to ensure complete removal of KUREZ DR VOX.

CLEAN-UP AND REMOVAL

Clean tools and equipment with warm, soapy water before KUREZ DR VOX dries.

The use of a heavy-duty floor cleaner such as EUCO CLEAN & STRIP is recommended to aid cleaning and removal. Scrub the floor with the cleaner and stiff bristle mechanical equipment, then rinse well with clean water. Heavy-duty mechanical means may also be used for removal, such as heavy-duty water blasting or abrasive methods like sanding or grinding. After proper clean-up, follow the instructions of the sealer, coating or covering manufacturer for the recommended surface preparation for the particular product to be applied. The use of KUREZ DR VOX does not eliminate the need to adequately clean and prepare the surface to assure good adhesion of the applied product, particularly when concrete or terrazzo toppings are to follow.

PRECAUTIONS/LIMITATIONS

- Do not allow containers of this product to freeze.
- Store between 50 °F to 90 °F (10 °C to 32 °C).
- For best application results, product temperature should be between 50 °F to 90 °F (10 °C to 32 °C) with ambient and surface temperatures between 45 °F to 100 °F (7 °C to 38 °C).
- After application, KUREZ DR VOX must remain uncovered and unprotected for proper dissipation.
- Do not apply at temperatures below 40 °F (4 °C).
- Do not use as bond breaker for tilt-up construction.
- Do not subject to rain or water for 4 hours after application.
- Not intended for use on architectural concrete panels unless complete removal is planned.
- Do not thin this product with water or other solvents.
- Longer dissipation times can be expected if the product is not exposed to traffic & sunlight or if the product is applied heavily or unevenly.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.25

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.